

## PRODUCT DESCRIPTION

Stongard MR is a nominal 0.75 to 1 mm thick flooring system created for positive side waterproofing applications. It is designed to protect areas below mechanical rooms, pump and mezzanine floors. It is comprised of:

### Stonproof ME7

A two-component, free-flowing, 100% solids, urethane, elastomeric waterproof membrane

### Stonkote HT4

A two-component, 100% solids, general purpose, epoxy coating

## OPTIONS

### Cove Base

Provides an integral seal at the joint between the floor and the wall. Cove bases in heights from 5 to 15 cm are available.

### Fiberglass Reinforcement

Incorporate fiberglass into the system to aide in crack bridging properties.

### Texture

Can be added to the system to provide slip resistance and wear properties.

**Note:** Some options can effect Physical Characteristics listed on the Product Data.

## PACKAGING

Stongard MR is packaged in units for easy handling. Each unit consists of:

### Stonproof ME7

1 carton containing:  
6 foil bags of Isocyanate

1 carton containing:  
6 poly bags of Polyol

### Stonkote HT4

0.75 cartons containing:  
4 foil bags of Amine  
4 poly bags of Resin

## COVERAGE

Each unit of Stongard MR will cover approximately 27.9 m<sup>2</sup> of surface at a nominal 0.75 to 1 mm.

## STORAGE CONDITIONS

Store all components of Stongard MR between 16 to 30°C in a dry area. Avoid excessive heat and do not freeze. The shelf life for epoxy primers/coatings is 3 years; the shelf life for Stonproof ME7 is 2 years in the original, unopened container.

## COLOR

Stongard MR is available in 12 standard colors. Custom colors are available upon request.

## SUBSTRATE

Stongard MR, in conjunction with the proper primers, is suitable for application over properly prepared concrete, metal or wood. For questions regarding other possible substrates or an appropriate primer, contact your local Stonhard representative or Technical Service.

## SUBSTRATE PREPARATION

Proper preparation is critical to ensure an adequate bond and system performance. The substrate must be dry and properly prepared utilizing mechanical methods. Questions regarding substrate preparation should be directed to your local Stonhard representative or Technical Service.

## PHYSICAL CHARACTERISTICS

<b>Tensile Strength</b> (ASTM D-412)	8,3 N/mm <sup>2</sup>
<b>Elongation</b> (ASTM D-412)	200%
<b>Hardness</b> (ASTM D-2240, Shore A)	70
<b>Theoretical Coverage.</b>	27.87 m <sup>2</sup>
<b>Pot Life</b> (@25°C)	30 to 35 minutes
<b>Abrasion Resistance.</b> (ASTM D-4060, CS-17)	0.06 gm
<b>Water Absorption.</b> (ASTM C-413)	0.1%
<b>VOC Content</b> (ASTM D-2369)	Stonproof ME7 - 8 g/l Stonkote HT4 - 30 g/l
<b>Cure Rate</b> (@25°C)	8 to 10 hours for tack-free surface 24 hours for normal operations

**Note:** The above physical properties were measured in accordance with the referenced standards. Samples of the actual floor system, including binder and filler, were used as test specimens. All sample preparation and testing is conducted in a laboratory environment, values obtained on field applied materials may vary and certain test methods can only be conducted on lab-made test coupons.

## PRIMING

The use of Standard Primer and SL Primer is necessary for all applications of Stongard MR over all substrates except Stonset grouts. Over Stonset grouts, Stonhard's Stonset Primer is used. Please see the appropriate primer Product Data sheet for details.

## MIXING

- Proper mixing is critical for the product to exhibit the proper application properties, cure properties and ultimate physical properties.
- Mechanical mixing using a slow-speed drill and mixing blade.
- See Stongard MR Directions for further details.

## APPLYING


- DO NOT attempt to install material if the temperature of Stongard MR components and substrate are not within 16 to 30°C. The cure time and application properties of the material are severely affected at temperatures outside of this range.
- Material must be applied immediately after mixing.
- Detailed application instructions can be found in the Stongard MR Directions.

## NOTES

- Procedures for maintenance of the flooring system during operations are described in the Stonkleen Floor Cleaning Procedures Brochure.
- Specific information regarding chemical resistance is available in the Stonkote HT4 Product Data sheet.
- Safety Data Sheets for Stongard MR are available online at [www.stoncor-europe.com](http://www.stoncor-europe.com) under Products or upon request.
- A staff of technical service engineers is available to assist with installation or to answer questions related to Stonhard flooring products.
- Requests for technical service or literature can be made through local sales representatives and offices, or corporate offices located worldwide.
- The appearance of all floor, wall and lining systems will change over time due to normal wear, abrasion, traffic and cleaning. Generally, high gloss coatings are subject to a reduction in gloss, while matte finish coatings can increase in gloss level under normal operating conditions.
- Surface texture of resinous flooring surfaces can change over time as a result of wear and surface contaminants. Surfaces should be cleaned regularly and deep cleaned periodically to ensure no contaminant buildup occurs. Surfaces should be periodically inspected to ensure they are performing as expected and may require traction-enhancing maintenance to ensure they continue to meet expectations for the particular area and conditions of use.

## CE MARKING

The harmonized European Standard EN 13813 „Screed material and floor screeds- Screed materials - Properties and requirements“ specifies the requirements for screed materials for use in floor construction internally. Resinous flooring systems as well as resinous screeds fall under this specification they have to be CE-labeled as per **Annex ZA., Table ZA.1.5 and 3.3** and fulfill the requirements of the given mandate of the Construction Products Regulation no. 305/2011.

	
StonCor Europe Rue du Travail 9 1400 Nivelles, Belgium	
13	
DOP-2013.08.002	
EN 13813 SR-AR1.0-B2.0	
Synthetic resin flooring system for use internally in buildings (system as per Product Data Sheet)	
Reaction to fire:	B <sub>fl</sub> -S <sup>1</sup>
Release of corrosive substances:	SR
Wear resistance:	AR1.0
Adhesion strength by pull-off:	> B2.0
Chemical resistance:	CRG <sup>1</sup>
<sup>1</sup> CRG: see Stonhard Chemical Resistance Guide	

## IMPORTANT:

Stonhard believes the information contained here to be true and accurate as of the date of publication. Stonhard makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

Rev. 1/17  
© 2017 Stonhard [www.Stoncor-europe.com](http://www.Stoncor-europe.com)

# STONHARD®

## European Offices:

Belgium	+32 674 93 710	Spain	+34 933 623 785	Germany	+49 240 541 740
France	+33 160 064 419	Portugal	+351 227 535 642	The Netherlands	+31 165 585 200
Poland	+48 422 112 768	United Kindom	+44 125 63 36 600	Italy	+39 022 53 751
		East Europe	+48 422 112 768		